



EN 15651-1:2012: Type F: EXT-INT-CC; 25LM Sealant for façade for interior and exterior application, intended for use in cold climate.

EN 15651-2:2012: Type G-CC; 25LM Sealant used for sealing glazing applications, intended for use in cold climate.

EN 15651-3:2012: Type S; XS1 Sealant for sanitary joints.

EN 15651-4:2012: Type PW: INT; 25LM Sealant used for pedestrian walkways for interior application.

Type F: EXT-INT		Type G		Type S		Type PW: INT	
Reaction to fire	Class E	Reaction to fire	Class E	Reaction to fire	Class E	Reaction to fire	Class E
Release of chemicals dangerous to the environment	NPD	Release of dangerous chemicals to the environment	NPD	Release of dangerous chemicals to the environment	NPD	Release of dangerous chemicals to the environment	NPD
Water tightness and air tightness		Water tightness and air tightness		Water tightness and air tightness		Water tightness and air tightness	
Resistance to flow	≤ 3 mm	Resistance to flow	≤ 3 mm	Resistance to flow	≤ 3 mm	Resistance to flow	≤ 3 mm
Loss of Volume	≤ 10 %	Loss of Volume	≤ 10 %	Loss of Volume	≤ 20 %	Loss of Volume	≤ 10 %
Adhesion / cohesion at maintained extension after water immersion	NF	Elastic recovery	≥ 60 %	Tensile properties after water immersion	NF	Elastic recovery	≥ 70 %
Elastic recovery	≥ 70 %	Tensile properties- Secant modulus at 23°C	≤ 0,4 MPa	Microbiological growth	0	Tensile properties- Secant modulus at 23°C	≤ 0,4 MPa
Tensile properties- Secant modulus at 23°C	≤ 0,4 MPa	Tensile properties- Secant modulus at -20°C	≤ 0,6 MPa	Durability	Pass	Tensile properties- Secant modulus at -20°C	≤ 0,6 MPa
Tensile properties- Secant modulus at -20°C	≤ 0,6 MPa	Tensile properties at maintained extension	NF			Tensile properties at maintained extension	NF
Tensile properties at maintained extension	NF	Adhesion/cohesion at variable temperatures	NF			Adhesion/cohesion at variable temperatures	NF
Adhesion/cohesion at variable temperatures	NF	Adhesion / cohesion at maintained extension after water immersion	NF			Adhesion/cohesion at maintained extension after water immersion	NF
Durability	Pass	Adhesion/cohesion after exposure to heat, water and artificial light	NF			Tear resistance	NF
<b>TYPE F: EXT-INT-CC</b>		Resistance to compression	0,31 MPa			Durability	Pass
Tensile properties -secant modulus	≤ 0,9 MPa	Durability	Pass				
Tensile properties at maintained extension	NF	<b>TYPE G-CC</b>					
		Tensile properties- secant modulus	≤ 0,9 MPa				
		Adhesion/Cohesion at maintained extension	NF				