



TEKAMAL ALTEKS SCC 0-3

self-compacting grouting non-shrinkage mortar

SIST EN 1504-3: CC mortar for structural repair, class R4



TE Šoštanj: before grouting with Tekamal Alteks SCC 0-3



TE Šoštanj: after grouting with Tekamal Alteks SCC 0-3

 1404	
TKK Proizvodnja kemičnih izdelkov, Srpenica ob Soči d.d. Srpenica 1, 5224 Srpenica, Slovenija 12 1404-CPD-1407	
EN 1504-3 Mortar for structural repair of concrete, CC (hydraulic cement based mortar)	
Compressive strength:	Class R4
Chloride ion content:	≤ 0,05 %
Adhesive bond:	≥ 2,0 MPa
Resistance to carbonation:	Adequate
Elastic modulus:<0>	≥ 20 GPa
Thermal compatibility:	
Freezing-thawing	≥ 2,0 MPa
Capillary absorption:	≤ 0,5 kgm ⁻² h ^{-0,5}
Harmful substances:	Meets requirement 5.4.
Inflammability class:	Euroclass A1

PROPERTIES

Tekamal Alteks SCC 0-3 is a one-component dry mixture of cement, special sands, new generation superplasticizer - hyperplasticizer and other chemical admixtures which enable the fresh mortar self-compacting properties and swelling, as well as and compensation of the hardened mortar shrinkage. In this way risk of cracks formation is reduced and physical and mechanical properties as well as durability are improved.

In general it is recommended that an individual layer of **Tekamal Alteks SCC 0-3** be 9-50 mm thick. When applying thicker layers approx. 25-35 weight parts of large-particle sand can be added (e.g. 4-8 mm). To determine the right quantity of mixing water in order to achieve the required properties of fresh and hardener mortar, preliminary tests should be done for each application method!

FIELD OF APPLICATION

Tekamal Alteks SCC 0-3 is used wherever non-shrinking properties are important and where high strengths and high durability is required:

- Grouting machines, cranes;
- Anchoring;
- Protecting and repairing concrete constructions,
- Sealing rigid joints between concrete elements.

ADVANTAGES

Fresh mortar:

- Ready-to-use mixture: only the required amount of water is to be added at the construction site,
- Excellent workability – self-compacting,
- Easy to apply – built-in under its own weight,
- Swelling up to 5 vol. %.

Hardened mortar:

- Cement-based: excellent compatibility with substrate and high alkaline reinforcement protection;
- High strengths: adhesive, bending and compressive;
- Compensates for or reduces shrinkage significantly,
- Resistance to carbonation,
- Low capillary water absorption,
- High resistance to water penetration,
- Good resistance to:
 - changes in temperature,
 - the effects of cold and salt,
- Durability.

TEKAMAL ALTEKS SCC 0-3

self-compacting grouting non-shrinkage mortar
SIST EN 1504-3: CC mortar for structural repair,
class R4

**TECHNICAL DATA**

Property	Test	Unit	Standard requirement SIST EN 1504-3	Declared
Dry mixture				
Colour and appearance	Visual	-	-	Dark grey powder
Maximum size of aggregate particles	-	mm	-	9
Recommended thickness of a single layer:	-	mm	-	
- Min.				9
- Max.				50
Chloride ion content:	SIST EN 1015-17	%	≤ 0,05	≤ 0,05
Fresh mixture				
Mixing water	-	l	-	approx. 3.4 – 4.1 per 25 kg depending on the desired workability
Workability	SIST EN 13395-2	mm	-	600 ± 20 %
Workability time	-	min	-	approx. 30 – 45 depending on the quantity of mixing water and the temperature
Swelling	SIST EN 934-4	vol %	-	≥ 0 up to +5
Working temperature: mortar, substrate, environment	-	°C	-	+ 5°C do + 30°C, optimal: + 15°C do + 25°C

Property	Test	Unit	Standard requirement SIST EN 1504-3		Declared
Hardened mortar			Class		
Compressive strength - 28 days	SIST EN 12190	MPa	R4	≥ 45	≥ 60
Density	SIST EN 12190	kg/m ³	-	-	2200 ± 5 %
Adhesive bond, 28 days	SIST EN 1542	MPa	R4	≥ 2,0	≥ 2,0
Resistance to carbonation	SIST EN 13295	-	R4	d _k ≤ reference concrete (MC (0,45))	d _k ≤ reference concrete (MC (0,45))
Elastic modulus, 28 days	SIST EN 13412	GPa	R4	≥ 20	≥ 20
Capillary absorption:	SIST EN 13687-1	kgm ² h ^{-0.5}	R4	≤ 0,5	≤ 0,5
Thermal compatibility, Part 1: Adhesive bond after freezing and thawing in the presence of salt (50 cycles)	SIST EN 13057	MPa	R4	≥ 2,0	≥ 2,0
Freezing-thawing resistance (30 cycles)	SIST EN 1026, Anex 5	mg/mm ²	-	-	< 0,20

APPLICATION GUIDELINES• **SUBSTRATE PREPARATION**

The areas on which **Tekamal Alteks SCC 0-3** will be applied must be solid and free of dust, greasy spots, corrosion by-products, mould and other impurities. Any loose materials and remainings of old coatings must be removed mechanically by grinding, grit blasting or water blasting. The best way to prepare larger areas is to wash them with high pressure water jet. **Cleaned surface should be as rough as possible and well soaked - water saturated - but without any standing water or water film which would prevent Tekamal Alteks SCC 0-3 to adhere well to the old substrate.**

• **MORTAR PREPARATION**

The most appropriate way of preparing the mortar is by adding dry mortar into water during constant mixing: dry mortar is mixed into the part of water and then the rest of the water is added to get the desired workability. Depending on its quantity, the mortar mixture can be mixed using a slow speed drill and a paddle, special mortar mixer or a forced action concrete mixer. Free-fall mixers are less suitable. However, they can be used in order to ensure the mixer is wet prior to adding dry mortar, to add dry mortar slowly and to ensure the mortar is being mixed long enough.

Mix for at least 5 minutes or until a uniform mixture is obtained. Try to entrain as little air as possible. Leave mortar to rest for approx. 5-10 minutes, then remix it and apply. Workability time is 30-45 minutes; it depends on the quantity of mixing water used, the consistency of the obtained mixture and temperature. Remix from time to time.

Important: because it contains superplasticizer-hyperplasticizer **Tekamal Alteks SCC 0-3** is much more sensitive even to the small change in mixing water quantity than the ordinary **Tekamal Alteks 0-3**. Therefore it is much more important to add first the minimal recommended quantity of mixing water and only after the thorough mixing and resting time the additional water is added **CAUTIOUSLY!**

• **APPLICATION**

The method of applying **Tekamal Alteks SCC 0-3** depends on the type of works (grouting, anchoring, repairs, etc.) and on the quality of the surface the mortar is being applied to (roughness, cavities,...). With regard to the method chosen, we adapt mortar workability by adding a sufficient amount of water. The mortar is then being applied either manually by means of ordinary masonry tools or mechanically by means of grouting. In any of these cases we must ensure the mortar covers all surfaces being repaired or to fill all cavities that are being grouted. When mortar is being

TEKAMAL ALTEKS SCC 0-3

self-compacting grouting non-shrinkage mortar
SIST EN 1504-3: CC mortar for structural repair,
class R4



poured into formworks, these should be of high quality and should provide good stability and tightness in order to prevent leakages. Prior to mortar application, formworks should be covered with a very thin layer of **Unimaz O / O-3 / OW** oils or with **Unimaz E / EKO-conc.** emulsions. Mortar is always applied/poured slowly and from one side in order to fill in all the space and to prevent the formation of air »pockets«.

When repairing smaller surfaces (patching), the damaged areas should be cut at a minimum angle of 90° and maximum angle of 135° to reduce the possibility of debonding with the top surface of the adjacent sound surface as this leads to an uneven curing of mortar and to the formation of cracks on the contact between the old substrate and mortar.

When repairing concrete blocks (thin-layer overlaying), dilatation, working and border joints should be taken into account! To seal dilatation joints, the use of permanent elastic sealants such as **Tioelast KVZ, Tioelast KOS, Tekasil Neutral PROFI** or **Tekafleks MS 15** is recommended.

Surfaces repaired with **Tekamal Alteks SCC 0-3** can be easily coated with dispersion- or polymer-based protective coatings (acrylic, epoxy etc.) However, be careful that the repaired surfaces are sufficiently dry. In any case, we recommend you consult the coating producer.

• CURING

Freshly applied mortar should be protected against excessive evaporation (sun, high temperatures, wind, draught) for at least 7 days. In more unfavourable conditions the protection should be prolonged up to 10 days. The most adequate way of protection is periodic wetting or covering with a wet cloth made of felt or jute and polyethylene film, etc. In case the protection with water is not possible the use of **Kontrasol 22 V** or **Kontrasol NOVI** - curing and protection agents, suitable for fresh concrete and mortar - is recommended.

• CLEANING THE TOOLS AND OTHER ACCESSORIES

Tools and other accessories used during work should be thoroughly cleaned immediately after use!

ADDITIONAL RECOMMENDATIONS AND WARNINGS

- Do not apply mortar at temperatures below +5°C and above +35°C!
- Temperature affects workability, setting and hardening time. To achieve optimal results it is recommended the temperature of the concrete and/or metal substrate/formwork before and during the application and 48 hours after the application be 15-25°C.
- Low temperatures (below +10°C) prolong the setting and hardening time. Thus, it is recommended to store the mortar in heated places, to use warm mixing water (approx. 20-40°C) and to execute works during the warmest time of a day.
- In order to accelerate the setting time, **Cementol Omega P** - set accelerating admixture - can be added (approx. 1 % per mortar weight) or, to accelerate the setting time and ensure additional protection against potential freezing at the same time, a set accelerating admixture with the effect of antifreeze - **Cementol B NOVI** - can be added (approx. 1 % per mortar weight).
- High temperatures (above +30°C) shorten the setting and hardening time. Thus, it is recommended to store the mortar in cooled places, to use cold mixing water and to execute works during the coldest time of a day.
- Setting time can also be prolonged by adding a set retarding admixture **Cementol Retard R2** (approx. 0.2 % per mortar weight).
- Large surfaces exposed to more unfavourable conditions (high temperatures, wind, draught, low air humidity) and to a risk that insufficient protection is/will be provided, can be additionally protected against the formation of cracks due to plastic shrinkage by adding a shrinking reducing admixture **Cementol Antikontrakt T**

(approx. 0.25-0.5% per mortar weight).

- Technical characteristics indicated in the table apply for the original, prepacked **Tekamal Alteks SCC 0-3** and **NOT for Tekamal Alteks SCC 0-3 with sand or one of the admixtures added during mixing.** In cases when contractors decide to add sand or chemical admixtures to the mortar, they should do some preliminary tests in order to find out, if mortar changed in this way still meets the requirements for fresh and cured mortar.
- Use only originally packed, closed, non-damaged and adequately stored packs of mortar!
- Never apply mortar onto smooth, insufficiently roughened substrates! Never apply mortar onto smooth, insufficiently roughened substrates!
- Never apply mortar onto dry substrates!
- Never add water, dry mortar or sand to over-thickened mortar. Such mortar should be thrown away.
- During works follow the requirements of standard SIST EN 1504-10: Products and systems for the protection and repair of concrete structures – Part 10: Site application of products and systems and quality control of the works.
- For any additional information and explanations please contact our technical service.

CONSUMPTION

- approx. 20 kg/m²/cm or 2 kg of dry mortar per 1 L of wet mortar depending on the quantity of water added and on the smoothness of the surface.

PACKAGING

- 25 kg sacks

STORAGE

- Store the product in tightly closed package in a dry and well ventilated space in order to protect it against potential damage and damp.
- If stored in a dry place, in tightly closed and undamaged packaging the shelf life of the product is min. 1 year from the production date.
- The product may still be used after the date of expiry, but the characteristics important for the intended use have to be examined.

SAFETY PRECAUTIONS

- Because it contains cement, the product irritates the skin and eyes and may cause allergic reactions if it comes into contact with skin.
- When handling the product, protective gloves and goggles should be used.
 - Do not breathe in dry powder.
 - Use a protection mask when handling dry powder.
 - Eating, drinking or smoking during work is prohibited.
 - After finishing work, hands should be thoroughly washed with water.

WARNING

Instructions are given on the basis of examinations and technical experience of the firm. However, due to specific conditions and work methods, preliminary tests are advised for every type of use. Since we cannot influence the course of work, we cannot be held responsible for its quality.

Tekamal Alteks SCC 0-3 complies with the requirements of standard SIST EN 1504-3: Products and systems for the protection and repair of concrete structures – Part 3: Structural and non-structural repair: CC mortar for structural repair, class R4 (for methods based on principles: 3.2, 4.4, 7.1, 7.2).